



## ▼ POREX® Porous PTFE Materials

### PM1030

PARAMETERS	VALUE	UNIT OF MEASUREMENT
PORE SIZE	5 - 10	μ
POROSITY	45 - 55	%
AIR FLOW	2.3 – 6.8	l/hr/cm <sup>2</sup> (Δp 20mbar)
WATER INTRUSION PRESSURE	240 - 550	mbar
THICKNESS	3.00	mm ± 0.25

#### ADDITIONAL INFORMATION

Pore size value indicates largest pore detected by bubble point method.

Porosity is calculated by weight.

Airflow values determined from a 47mm Ø sample.

Can be Oleophobicly treated to Grade 8 by AATCC TM 118-1997.