



## ▼ POREX® Porous PTFE Materials

### PM21ML

PARAMETERS	VALUE	UNIT OF MEASUREMENT
PORE SIZE	12 - 16	μ
POROSITY	49	%
AIR FLOW	6.8 – 13.6	l/hr/cm <sup>2</sup> (Δp 10mbar)
WATER INTRUSION PRESSURE	210 - 480	mbar
THICKNESS	0.28	mm ± 0.03

#### ADDITIONAL INFORMATION

Laminated membrane.

Pore size value indicates largest pore detected by bubble point method.

Porosity is calculated by weight.

Airflow values determined from a 47mm Ø sample.

MS-PM21ML Rev. 4

**POREX**

©2018 Porex Corporation. Porex is a registered

**Porex Technologies**

500 Bohannon Road  
Fairburn, GA 30213 USA

E-mail: [infoPorex@porex.com](mailto:infoPorex@porex.com)

**Porex Technologies GmbH**

Sales & Marketing Europe  
Strangenhäuschen 30  
52070 Aachen, Germany

**Porex Technologies Ltd.**

Merlin House  
Ainess Point Business Park  
Ainess, Ross-shire IV17 0UP  
Scotland, United Kingdom

**Porex Technologies Sdn Bhd**

Lot P.T. 74, Jalan Hulu Tinggi 26/6  
Seksyen 26, Sektor A  
Hicom Industrial Park  
40400 Shah Alam