



## ▼ POREX® Porous PTFE Materials

### PM3030

PARAMETERS	VALUE	UNIT OF MEASUREMENT
PORE SIZE	15 - 40	μ
POROSITY	55 - 60	%
AIR FLOW	2.3 – 9.1	l/hr/cm <sup>2</sup> (Δp 10mbar)
WATER INTRUSION PRESSURE	70 - 280	mbar
THICKNESS	3.00	mm ± 0.25

#### ADDITIONAL INFORMATION

Pore size value indicates largest pore detected by bubble point method.

Porosity is calculated by weight.

Airflow values determined from a 47mm Ø sample.

Can be Oleophobicity treated to Grade 8 by AATCC TM 118-1997.

MS-PM3030 Rev. 2



©2010 Porex Corporation. Porex is a registered

#### Porex Technologies

500 Bohannon Road  
Fairburn, GA 30213 USA

E-mail: [infoPorex@porex.com](mailto:infoPorex@porex.com)

#### Porex Technologies GmbH

Sales & Marketing Europe  
Strangenhäuschen 30  
52070 Aachen, Germany

#### Porex Technologies Ltd.

Merlin House  
Alness Point Business Park  
Alness, Ross-shire IV17 0UP  
Scotland, United Kingdom

#### Porex Technologies Sdn Bhd

Lot P.T. 74, Jalan Hulu Tinggi 26/6  
Seksyen 26, Sektor A  
Hicom Industrial Park  
40100 Shah Alam