



POREX® Porous PTFE Materials

PM0530

PARAMETERS	VALUE	UNIT OF MEASUREMENT
PORE SIZE	4 - 6	μ
POROSITY	35 - 45	%
AIR FLOW	1.4 - 6.8	l/hr/cm ² (Δp 70mbar)
WATER INTRUSION PRESSURE	690 - 1240	mbar
THICKNESS	3.00	mm ± 0.25

ADDITIONAL INFORMATION

Pore size value indicates largest pore detected by bubble point method.

Porosity is calculated by weight.

Airflow values determined from a 47mm Ø sample.

Can be Oleophobic treated to Grade 8 by AATCC TM 118-1997.

MS-PM0530 Rev. 6

POREX

© 2011 Porex Corporation. Porex is a registered trademark of Porex Corporation. All rights reserved.

F-026 Rev. 2

www.porex.com

Porex Technologies

500 Briarwood Road
Fairburn, GA 30213 USA

E-mail: info@porex.com

T: +1 770 8641421

F: +1 770 8630954

Porex Technologies GmbH

Sales & Marketing Europe
Strängenhäuschen 30
52070 Aachen Germany

E-mail: info@porex.de

T: +49 241 9105250

F: +49 241 91052526

Porex Technologies Ltd.

Merrin House
Alness Point Business Park
Alness, Ross-shire IV17 0UP
Scotland United Kingdom

E-mail: info@ptporex.com

T: +44 1349 894080

F: +44 1349 894076

Porex Technologies Sdn Bhd

Lot P.T. 74, Jalan Huta Tinggi 78/6
Bakayan 26, Sektor A
Hiom Industrial Park
40400 Shah Alam
Selangor, Malaysia

E-mail: info@porex.com.my

T: +603 6191 3308

F: +603 5197 3308