



POREX® Porous PTFE Materials

PM6M

PARAMETERS	VALUE	UNIT OF MEASUREMENT
PORE SIZE	5	μ
POROSITY	40	%
AIR FLOW	3.6 – 7.3	l/hr/cm ² (Δp 20mbar)
WATER INTRUSION PRESSURE	650 - 1100	mbar
THICKNESS	0.1	mm ± 0.03

ADDITIONAL INFORMATION

Pore size value indicates largest pore detected by bubble point method.

Porosity is calculated by weight.

Airflow values determined from a 47mm Ø sample.

Can be Oleophobicity treated to Grade 8 by AATCC TM 118-1997

MS-PM6M Rev. 5

POREX

©2010 Porex Corporation. Porex is a registered

Porex Technologies

500 Bohannon Road
Fairburn, GA 30213 USA

E-mail: infoPorex@porrex.com

Porex Technologies GmbH

Sales & Marketing Europe
Strangenhäuschen 30
52070 Aachen, Germany

Porex Technologies Ltd.

Merlin House
Alness Point Business Park
Alness, Ross-shire IV17 0UP
Scotland, United Kingdom

Porex Technologies Sdn Bhd

Lot P.T. 74, Jalan Hulu Tinggi 26/6
Seksyen 26, Sektor A
Hicom Industrial Park
40400 Shah Alam