



# POREX<sup>®</sup> Porous PTFE Materials

## Material Datasheet

### MD10

PARAMETERS	VALUE	UNIT OF MEASUREMENT
BACTERIAL FILTRATION EFFICENCY	> 99.9%	ASTM F2101 <sup>1</sup> (nominal)
WATER ENTRY PRESSURE (WEP)	Min 175, Typical 270	mbar
AIR FLOW (ATEQ)	Min 70, Typical 125	l/hr/cm <sup>2</sup> Δp 70mbar
THICKNESS	0.13	mm (nominal)

### ADDITIONAL INFORMATION

- Can be supplied in format of:
  - Rolls (10mm-330mm width) on 75mm core
  - Sheets
  - Discs
- Assembly suggestions:
  - Ultrasonic welding
  - Thermal welding
  - Over-moulding
  - Pressure sensitive Adhesive
  - Compression seal
- Sterilisation method:
  - Steam/Autoclave (repeated use)
  - EtO
- Raw material is compliant with:
  - FDA 21CFR 177.1550
  - USP 28, NF 23, 2005, for USP Class VI Plastics at 70°C



<sup>1</sup> ASTM F2101 was adapted to employ a more severe challenge. Test conditions and data available on request.

#### Disclaimer

This standard sample is for evaluation of form, fit, and function to determine product specification requirements for custom products. Please reference the values in our data sheet for specification guidelines of standard products. In Vitro Diagnostic (IVD), medical-surgical and pharmaceutical samples are for investigational use only and subject to specific application, test condition and regulatory requirements.



Porex Corporation  
500 Bohannon Road,  
Fairburn, GA 30213  
USA

info@porex.com  
T. +1 770 964 1421  
F. +1 770 969 0954

Porex Technologies GmbH  
Strangenhäuschen 30,  
52070 Aachen,  
Germany

info@porex.de  
T. +49 241 910525-0  
F. +49 241 910525-16

Porex Technologies Ltd.  
Merlin House, Alness Point  
Business Park Alness,  
Ross-shire IV17 OUP,  
Scotland, UK

infoPTFE@porex.com  
T. +44 1349 884060  
F. +44 1349 884076

Porex Technologies Sdn Bhd  
Lot P.T. 74, Jalan Hulu Tinggi 26/6,  
Seksyen 26, Sektor A  
Hicom Industrial Park, 40400 Shah Alam,  
Selangor, Malaysia

info\_malaysia@porex.com  
T. +603 5191 3308  
F. +603 5192 3308

www.porex.com  
800.241.0195

MD-MD10 Rev. 2