



POREX® Porous PTFE Materials

PM3015

PARAMETERS	VALUE	UNIT OF MEASUREMENT
AIR FLOW	≥ 3.6	l/hr/cm ² (Δp 10mbar)
WATER INTRUSION PRESSURE	≥ 40	mbar
THICKNESS	1.50	mm ± 0.25

ADDITIONAL INFORMATION

Airflow values determined from a 47mm Ø sample.

Can be Oleophobicity treated to Grade 8 by AATCC TM 118-1997.

Porex Technologies

500 Bohannon Road
Fairburn, GA 30213 USA

E-mail: infoPorex@porex.com

T. +1 770 9641421
F. +1 770 9690954

Porex Technologies GmbH

Sales & Marketing Europe
Strangenhäuschen 30
52070 Aachen, Germany

E-mail: infoPorex@porex.de

T. +49 241 9105250
F. +49 241 91052526

Porex Technologies Ltd.

Merlin House
Alness Point Business Park
Alness, Ross-shire IV17 0UP
Scotland, United Kingdom

E-mail: infoPTFE@porex.com

T. +44 1349 884060
F. +44 1349 884076

Porex Technologies Sdn Bhd

Lot P.T. 74, Jalan Hulu Tinggi 26/6
Seksyen 26, Sektor A
Hicom Industrial Park
40400 Shah Alam,
Selangor, Malaysia

E-mail: infoPorex@porex.com.my

T. +603 5191 3308
F. +603 5192 3308